


Shell Sarawax SX 50



Synthetic paraffin. It contains an effective oxidation inhibitor.

Product data

Properties	Standard	Unit	Specification
Congealing point	DIN ISO 2207	°C	50 – 56
Penetration at 25 °C	DIN 51 579	0.1 mm	22– 40
Oil content	DIN ISO 2908	%	max. 2,8
Viscosity at 100 °C	DIN 51 562 / T1	mm ² /s	typ. 3.3
Color, Saybolt	DIN 51 411	-	min. +28
Color	visual	-	white
Density at 70 °C	DIN 51 757	kg/m ³	764
Purity requirement FDA	§ 172.886	-	complies
Purity requirement EUR. Pharm.	Eur. Pharm.	-	complies
Purity requirement candle industry	RAL-GZ 041	-	complies

We reserve the right to change the specification as a result of technical progress or for reasons related to production!
No guarantee or warranty is implied as to any particular applications of our products.